

ER80S-D2

LOW ALLOY HIGH TENSILE SOLID WIRES



SIZE	0.9mm	1.2mm	1.6mm
AMPS	75-200A	90-350A	170-390A

CHARACTERISTICS

- 1, Superior arc stability
- 2, Low spatter level and a flat bead with excellent appearance
- 3, High ductility, excellent impact values and tensile strengths of the bead

TYPICAL APPLICATIONS

- 1, Farm implements
- 2, Automotive parts, pipes, light-gauge steels
- 3, Low alloy steels such as AISI 4130 and high yield steels such as T-1.

CLASSIFICATION

AWS A5.28 ER80S-D2

CHEMICAL COMPOSITIONS (Wt%), ALL WELD METAL, TYPICAL

C	Si	Cu	Mn	Mo	P	S
0.08	0.70	0.15	1.90	0.5	0.01	0.009

WELDING POSITIONS (ISO/ASME)



AVAILABLE SIZES (DIA.)

0.9mm/1.2mm/1.6mm

EQUIVALENT TO

PACKAGING DETAILS

1/5/15kg Spools 250/350kg Drums

CURRENT TYPE

DC+

MECHANICAL PROPERTIES, ALL WELD METAL, TYPICAL

Condition	Shielding Gas	Yield Strength (mpa)	Tensile Strength (mpa)	Elongation(%)	Charpy V notch(J)
AW	80% Ar + 20% CO2	570	660	22	-20 C 88

