

E71T-1C/M

TecMig
The pro's choice

MILD-STEEL FLUX CORED WIRES, DUAL USE

TYPICAL APPLICATIONS

1. Shipbuilding
2. General Fabrication
3. Structure Fabrication
4. Pressure Vessels

CHARACTERISTICS

1. Fast freezing slag for out-of-position welding
2. Premium arc performance and bead appearance.
3. All positional welding capability
4. Comply with AWS D1.8 seismic lot waiver requirements



SIZE	AMPS
1.2mm	140-300A
1.6mm	180-400A

CLASSIFICATION

AWS A5.20 E71T-1C/M
 AWS A5.36 E71T1-C1/M21A2-CS1-H8
 EN ISO17632-A-T 42 0 P C 1

CHEMICAL COMPOSITIONS (Wt%), ALL WELD METAL, TYPICAL

C	Mn	Si	S	P
0.08	1.42	0.92	0.012	0.015

WELDING POSITIONS (ISO/ASME)



AVAILABLE SIZES (DIA.)

1.0mm/1.2mm/1.6mm

EQUIVALENT TO

Lincoln Outershield 71 Elite Esab OK E71T-1
 Infra Frontiarc 711 Indura 71T-1
 BÖHLER E71T-1C/1M

PACKAGING DETAILS

5kg /15kg Spools, Vacuum pack ; 250kg Drums

CURRENT TYPE

DC+

MECHANICAL PROPERTIES, ALL WELD METAL, TYPICAL

Condition	Shielding Gas	Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation(%)	Charpy V notch (J)
AW	100% CO ₂	490	578	28	-20 C 92
	80% Ar+20% CO ₂	506	590	28	-20 C 104

Note:

- ① Shielding gas: 100% CO₂ or 80% Ar+20% CO₂; Gas speed 15-25L/Min.
- ② Wire extension length 15-25mm.

